

DUPOTOP
Films

*Flagship Window Film
Series*



MAGNETRON SPUTTERING



CATALOG

MAGNETRON SPUTTERING

DMS-7095



— V7095-PSA Sample
— V7095-SR Sample
— V7095-T Sample

S
P
E
C
I
F
I
C
A
T
I
O
N
S



Infrared Rejection (950nm)	95%	Ultraviolet Rejection	99%	Visible Light Transmission	68%
Infrared Rejection (1400nm)	99%	Thickness	52±2 μm	Total Solar Energy Rejection (TSER)	50.6%
PSA Visible Light Reflectance	7.5%	Shading Coefficient	0.56%	Total Solar Transmittance	35.1%
SR Visible Light Reflectance	8.6%	Haze	<1%	Total Solar Reflectance	5.6%

dupotopfilms.com

DUPOTOP
Films

MAGNETRON SPUTTERING

DMS-5095



— V5095-PSA Sample
— V5095-SR Sample
— V5095-T Sample

S
P
E
C
I
F
I
C
A
T
I
O
N
S


Infrared Rejection (950nm)	95%	Ultraviolet Rejection	99%	Visible Light Transmission	45%
Infrared Rejection (1400nm)	98%	Thickness	52±2 μm	Total Solar Energy Rejection (TSER)	58.5%
PSA Visible Light Reflectance	9.7%	Shading Coefficient	0.47%	Total Solar Transmittance	25.6%
SR Visible Light Reflectance	11.6%	Haze	<1%	Total Solar Reflectance	8.4%

dupotofilms.com

DUPOTOP
Films

MAGNETRON SPUTTERING

DMS-3595



— V3595-PSA.Sample
— V3595-SR.Sample
— V3595-T.Sample

S
P
E
C
I
F
I
C
A
T
I
O
N
S


Infrared Rejection (950nm)	95%	Ultraviolet Rejection	99%	Visible Light Transmission	33%
Infrared Rejection (1400nm)	98%	Thickness	52±2 μm	Total Solar Energy Rejection (TSER)	61.7%
PSA Visible Light Reflectance	8.9%	Shading Coefficient	0.43%	Total Solar Transmittance	21.3%
SR Visible Light Reflectance	9.3%	Haze	<1%	Total Solar Reflectance	8.4%

dupotopfilms.com

DUPOTOP
Films

MAGNETRON SPUTTERING

DMS-2095



S
P
E
C
I
F
I
C
A
T
I
O
N
S


Infrared Rejection (950nm)	95%	Ultraviolet Rejection	99%	Visible Light Transmission	22%
Infrared Rejection (1400nm)	99%	Thickness	52±2 μm	Total Solar Energy Rejection (TSER)	67.7%
PSA Visible Light Reflectance	6.9%	Shading Coefficient	0.36%	Total Solar Transmittance	12.9%
SR Visible Light Reflectance	6.2%	Haze	<1%	Total Solar Reflectance	6.5%

dupotofilms.com

DUPOTOP
Films

MAGNETRON SPUTTERING

DMS-0595



— V0595-PSA Sample
— V0595-SR Sample
— V0595-T Sample

S
P
E
C
I
F
I
C
A
T
I
O
N
S

Infrared Rejection (950nm)	95%	Ultraviolet Rejection	99%	Visible Light Transmission	6%
Infrared Rejection (1400nm)	97%	Thickness	52±2 μm	Total Solar Energy Rejection (TSER)	71.6%
PSA Visible Light Reflectance	6.8%	Shading Coefficient	0.32%	Total Solar Transmittance	7.6%
SR Visible Light Reflectance	5.6%	Haze	<1%	Total Solar Reflectance	6.4%

dupotofilms.com

DUPOTOP
Films